

(Code: H10)

High performance EVA materials

Appearance	Color	Application
Granulated	Variety of colors	Slippers

Property	Unit	Value
Hardness	shoreA	41 ± 1
Melting temprature	°C	103 ± 2
Ash content	%	17/5
Injection time	s	17 ± 1
Mold temprature	°C	180-200
Cylinder temprature	°C	98-103
Activation temprature of the foaming agent	°C	170-200