

## (Code: H20)

### High performance EVA materials

Appearance	Color	Application
Granulated	Variety of colors	Slippers

Property	Unit	Value
Hardness	shoreA	36 ± 1
Melting temprature	°C	100 ± 2
Ash content	%	15
Injection time	s	15 ± 2
Mold temprature	°C	180-200
Cylinder temprature	°C	95-100
Activation temprature of the foaming agent	°C	170-200