

## (Code: K10)

### High performance EVA materials

Appearance	Color	Application
Granulated	Variety of colors	Insole

Property	Unit	Value
Hardness	shoreA	55 ± 1
Melting temprature	°C	108 ± 2
Ash content	%	19/63
Injection time	s	22 ± 2
Mold temprature	°C	180-200
Cylinder temprature	°C	100-105
Activation temprature of the foaming agent	°C	160-200